

MAVR-000120-1411

Rev. V6

Features

- Usable Past 70 GHz
- · Constant Gamma for Linear Tuning
- Low Parasitic Capacitance
- High Q
- Silicon Nitride Passivation
- Polyimide Scratch Protection
- Surface Mount Configuration
- Lead Free (RoHs Compliant)
- · Available in Pocket Tape and Reel
- Can withstand 500 Temperature Cycles (-65°C to +150°C), mounted with 96.5 Sn/3.5 Ag solder without Mechanical Degradation.
- Can be Mounted with Solder or Conductive Epoxy


Description

The MAVR-000120-1411 is a gallium arsenide flip chip hyperabrupt varactor diode. This device is fabricated on OMCVD epitaxial wafers using a process designed for high device uniformity and extremely low parasitics. This diode is fully passivated with silicon nitride and has an additional layer of polyimide for scratch protection. The protective coatings prevent damage to the junction during automated or manual handling. The flip chip configuration is suitable for pick and place insertion.

Ordering Information

| Part Number | Package | |
|--------------------|-------------|--|
| MAVR-000120-14110P | Pocket Tape | |
| MAVR-000120-14110G | Gel Pack | |

Chip Layout




Front View (Circuit Side)



Back View (Operator Side)

Schematic



Flip Chip Tuning Varactor Equivalent Circuit



MAVR-000120-1411

Rev. V6

Electrical Specifications @ T_A = +25°C

Breakdown Voltage @ I_R = 10 μ A, V_b = 20 V Minimum Reverse Leakage Current @ V_R =14 V, I_R = 100 nA Maximum

| Parameter | Test Conditions | Units | Min. | Тур. | Max. |
|-------------------|---|-------|------------------|----------------|------------------|
| Total Capacitance | $V_R = 0 V, 1 MHz$ $V_R = 4 V, 1 MHz$ $V_R = 10 V, 1 MHz$ | pF | 0.30 0.14 | -1.1 — — | 0.40 0.20 |
| Q Factor | V _R = 4 V, 50 MHz | pF | 3000 | _ | |
| Gamma | V _R = 2 - 12 V | pF | 0.9 | _ | 1.1 |


Absolute Maximum Ratings^{1,2}

| Parameter | Absolute Maximum | |
|-----------------------|------------------|--|
| Power Dissipation | 100 mW | |
| Operating Temperature | -40°C to +125°C | |
| Storage Temperature | -65°C to +150°C | |
| Storage Temperature | +260°C | |

^{1.} Exceeding any one or combination of these limits may cause permanent damage to this device.

Typical Performance Curves @ +25°C

Capacitance vs. Voltage Gamma = 1.00 +/- 10% (2 - 12 V)



^{*} Specifications are subject to change without prior notification

MACOM does not recommend sustained operation near these survivability limits.



MAVR-000120-1411

Rev. V6

Mounting Techniques

Die attach for these devices is made simple through the use of surface mount die attach technology. This chip was designed to be inserted onto hard or soft substrates with the junction side down. This chip can be mounted with conductive epoxy or with solder.

Solder Die Attach:

This device can be mounted with Sn63/Pb37 or RoHS compliant solder. Typical reflow profiles are provided on MACOM application note M538, "Surface Mounting Instructions" which can be found @ www.macom.com

Epoxy Die Attach:

This device can also be attached with conductive epoxy. The assembly can be preheated to 125°C - 150°C. Use a minimum amount of epoxy. Cure epoxy as per manufacturer's instructions.

Handling Procedures

The following precautions should be observed to avoid damaging these chips:

Cleanliness:

The chips should be handled in a clean environment. Do not attempt to clean die after installation.


Static Sensitivity:

Semiconductor devices are ESD sensitive and can be damaged by static electricity. Proper ESD techniques should be used when handling these devices.

General Handling:

The protective polymer coating on the active areas of these die provides scratch protection, particularly for the metal air bridge which contacts the anode. Die can be handled with tweezers or vacuum pickups and are suitable for use with automatic pick-and-place equipment.

Outline Drawing Flip Chip (Case Style 1500)



| Dim. | Inches | | Millimeters | | |
|------|--------|--------|-------------|-------|--|
| | Min. | Max. | Min. | Max. | |
| Α | 0.015 | 0.017 | 0.381 | 0.431 | |
| В | 0.029 | 0.031 | 0.736 | 0.787 | |
| С | 0.008 | 0.009 | 0.203 | 0.228 | |
| D | 0.007 | 0.008 | 0.178 | 0.203 | |
| E | 0.016 | 0.017 | 0.406 | 0.431 | |
| F | 0.006 | 0.007 | 0.152 | 0.178 | |
| G | 0.0075 | 0.0085 | 0.190 | 0.216 | |
| Н | 0.0075 | 0.0085 | 0.190 | 0.216 | |

Pad finish is 0.2 microns of gold over 4 microns of nickel.



MAVR-000120-1411

Rev. V6

MACOM Technology Solutions Inc. ("MACOM"). All rights reserved.

These materials are provided in connection with MACOM's products as a service to its customers and may be used for informational purposes only. Except as provided in its Terms and Conditions of Sale or any separate agreement, MACOM assumes no liability or responsibility whatsoever, including for (i) errors or omissions in these materials; (ii) failure to update these materials; or (iii) conflicts or incompatibilities arising from future changes to specifications and product descriptions, which MACOM may make at any time, without notice. These materials grant no license, express or implied, to any intellectual property rights.

THESE MATERIALS ARE PROVIDED "AS IS" WITH NO WARRANTY OR LIABILITY, EXPRESS OR IMPLIED, RELATING TO SALE AND/OR USE OF MACOM PRODUCTS INCLUDING FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, INFRINGEMENT OF INTELLECTUAL PROPERTY RIGHT, ACCURACY OR COMPLETENESS, OR SPECIAL, INDIRECT, INCIDENTAL, OR CONSEQUENTIAL DAMAGES WHICH MAY RESULT FROM USE OF THESE MATERIALS.

MACOM products are not intended for use in medical, lifesaving or life sustaining applications. MACOM customers using or selling MACOM products for use in such applications do so at their own risk and agree to fully indemnify MACOM for any damages resulting from such improper use or sale.